

HUNTSMAN

Enriching lives through innovation

Shaping the future

TPU elastomers for
Molding applications





Experts in elastomers

Our polyurethanes business division is a leading developer of polyurethane (PU) and thermoplastic polyurethane (TPU) materials. Combining global reach with decades of experience in material innovation, we are experts in urethane-based elastomers and have in-depth knowledge of their application across a vast range of industries.

A flexible partner for plastics molders

We are a leading provider of TPU elastomers that can help meet the manufacturing challenges of a fast-paced world. Tough and reliable, yet incredibly versatile, our TPU elastomers can be easily injection molded or overmolded and are renowned for their extreme adaptability.

We offer:

- **IROGRAN® TPU elastomers** – a range of premium injection molding elastomers for demanding industrial applications
- **AVALON® TPU elastomers** – a portfolio of elastomers well suited to the manufacture of consumer products and general-purpose applications.

Through our Tecnoelastomeri business, we provide a wide range of off-the-shelf and custom made hot-cast elastomers. Under our **TECNOTHANE®** and **DALTOCAST®** brands, we offer hot-cast elastomers that provide good chemical resistance and excellent mechanical characteristics. This includes engineering elastomers, which are exceptionally resilient and designed for use in extreme working conditions.

We also make our own range of high performance **CASTECH™** casting machines. These machines are used for processing hot cast elastomer systems including our **TECNOTHANE®** range.

For more information, go to www.tecnoelastomeri.com or refer to the Huntsman Tecnoelastomeri brochure.

Shaping the future

Our IROGRAN® and AVALON® TPU elastomers for specialty molding applications range from 55 Shore A to 65 Shore D hardness and can be adapted to suit different production techniques.

Regardless of their application, our injection molding elastomers are renowned for their mechanical and physical properties including:

- Wear and tear strength
- Dimensional stability
- Hydrolysis and oil resistance
- Low compression set
- Dynamic load performance
- Elasticity and flexibility down to -50°C
- Processing consistency with perfect surface definition
- Processing speed with up to 30% quicker demolding than industry standard materials
- Excellent slip resistance (specialty grades)
- Transparency and translucency (specialty grades)
- Recyclability.

Key applications

Industrial

- Hydraulic and pneumatic seals and gaskets
- Wheels, pulleys, sprockets, castors, rollers
- Bladders
- Handles for industrial equipment
- Agricultural parts for sorting and sowing equipment
- Parts for construction tools and machinery
- Mineral extraction and mining screens.

Transportation & automotive

- Automotive dashboard parts
- Other interior components e.g., trays, gear knobs, cup holders, buttons
- Over-molded key cases
- Technical parts such as spring aids
- Stone protection parts
- Reusable automotive packaging or dunnage.

Consumer goods

- Soft-touch handles and wheels
- Protection cases for electrical equipment
- Sports equipment
- Nose pads for glasses / eyewear
- Durable furniture parts.



Product highlights

IROGRAN® TPU elastomers

IROGRAN® TPU A 70 E 4675:

Exceptional performance in over-molding

IROGRAN® A 70 E 4675 elastomer is a unique, soft, plasticizer-free, polyester TPU for injection molding applications. Easily processed, and with an exceptionally short cycle time, IROGRAN® A 70 E 4675 TPU is used extensively across a wide range of industries including the production of specialized automotive, sports and consumer goods.

IROGRAN® TPU A 92 E 4246:

For thick wall parts with a short cycle time

Within our injection molding product range, IROGRAN® A 92 E 4246 TPU is one of the best performing polyester-based elastomers that we offer. With an increased degree of crystallinity, this elastomer grade is ideally suited to the creation of thick walled parts, where short cycle times and fast demolding rates are a prerequisite.

IROGRAN® TPU A 92 E 4860:

Improved hydrolysis and excellent melt strength

IROGRAN® A 92 E 4860 TPU is a great elastomer choice for extrusion and injection blow molding projects. High crystallinity gives this polyester-based material the melt strength needed for these special processes and for the production of bellows and other blow molded parts. This TPU grade also offers a short cycle time compared to standard grades.

Product highlights

AVALON® TPU elastomers

AVALON® TPU 95 AHT:

A high transparency TPU elastomer

AVALON® 95 AHT TPU is a colorless, high transparency, TPU elastomer. Offering excellent UV and abrasion resistance, this durable elastomer is frequently used in the production of consumer goods such as footwear and protective covers for mobile phones and tablets.

AVALON® TPU 95 ABR:

A TPU elastomer with high abrasion resistance

This polyester-based TPU forms part of a family of products designed for applications that require the lowest possible abrasion loss. Offering good cut and scratch resistance, alongside low temperature performance and short cycle times, AVALON® 95 ABR TPU is widely used to produce objects including escalator wheels and sports shoe soles.

AVALON® TPU 55 AHG:

A soft, phthalate-free TPU elastomer

Part of the AVALON® soft range, AVALON® 55 AHG TPU is a polyester-based elastomer system for injection molding applications. Offering a broad processing window and a short cycle time compared to other soft TPU grades, this elastomer offers all the usual physical properties expected of a TPU including good abrasion resistance.

Infinite scope for innovation

IROGRAN® TPUs: Key products



Physical properties	Norm	Unit	A 60 E 4612 N	A 70 H 4673 N	A 70 E 4675	A 80 H 4698	A 87 H 4615	A 92 E 4860	A 92 E 4246	A 92 H 4656	A 95 E 4813	A 95 H 4678	A 98 E 4066	A 98 H 4661	A 65 P 4324 N	A 80 P 5039	A 85 P 4394	A 92 P 4207	A 92 P 4637	A 95 P 5044	A 98 P 4535	Unit	Norm	Physical properties		
			IROGRAN® ester-based										IROGRAN® ester-based						IROGRAN® ether-based							
GENERAL																										
Hardness	ISO 7619	Shore A	65	74	75	81	85	91	92	93	95	95	97	96	71	80	85	92	92	95	96	Shore A	ISO 7619	Hardness		
Hardness	ISO 7619	Shore D	18	25	25	31	35	42	44	40	44	45	49	52	22	29	36	40	39	48	51	Shore D	ISO 7619	Hardness		
Density	ISO 1183-1	g/cm³	1,17	1,18	1,15	1,19	1,20	1,20	1,21	1,21	1,21	1,23	1,22	1,23	1,12	1,10	1,12	1,14	1,13	1,14	1,16	g/cm³	ISO 1183-1	Density		
MECHANICAL																										
Tensile strength	DIN 53504	MPa	31	35	30	47	45	49	50	45	41	45	50	50	30	32	45	49	45	55	55	MPa	DIN 53504	Tensile strength		
Elongation @ break	DIN 53504	%	900	790	650	650	640	600	610	550	550	540	530	520	800	720	640	570	600	500	510	%	DIN 53504	Elongation @ break		
Tensile stress @ 100% elongation	DIN 53504	MPa	2,7	3,1	3,3	4,6	5,6	7,5	7,2	8,9	10	11,1	11,4	16	3,9	4,6	7	9,5	9,1	12,3	15,4	MPa	DIN 53504	Tensile stress @ 100% elongation		
Tensile stress @ 300% elongation	DIN 53504	MPa	5	7,5	5,8	12,7	11,1	16	15	18,6	17,5	19,8	25	27,7	9,8	8,7	12	16,6	15,9	30,7	25	MPa	DIN 53504	Tensile stress @ 300% elongation		
Tear strength	ISO 34-1	N/mm	35	50	35	85	80	85	90	100	105	115	135	125	35	45	60	75	74	101	120	N/mm	ISO 34-1	Tear strength		
Compression set 70h @ 23°C	ISO 815	%	17	-	35	19	25	25	25	25	25	24	30	25	25	23	20	28	25	30	32	%	ISO 815	Compression set 70h @ 23°C		
Compression set 24h @ 70°C	ISO 815	%	43	-	58	40	43	39	50	43	45	43	45	46	48	43	40	44	41	82	50	%	ISO 815	Compression set 24h @ 70°C		
Mold shrinkage	ISO 294-4	%	3	2	1,6	0,6	1,1	0,9	0,9	0,6	0,8	0,7	0,7	0,7	1,2	0,9	0,8	0,8	0,9	0,7	0,8	%	ISO 294-4	Mold shrinkage		
Bayshore rebound resilience	ASTM D-2632	%	54	50	25	42	40	33	32	32	-	30	30	28	58	47	36	34	34	35	30	%	ASTM D-2632	Bayshore rebound resilience		
Abrasion	ISO 4649	mm³	55	45	90	30	25	30	25	30	30	30	30	35	60	30	25	25	30	30	30	mm³	ISO 4649	Abrasion		
THERMAL																										
TMA low melt range	Huntsman	°C	140	-	150	155	135	180	175	170	170	180	185	190	110	145	150	165	160	175	185	°C	Huntsman	TMA low melt range		
TMA high melt range	Huntsman	°C	170	-	190	165	185	200	190	185	200	190	200	200	165	155	170	188	170	187	200	°C	Huntsman	TMA high melt range		
OTHER FEATURES																										
Transparent				x		x										x				x				Transparent		
Highly crystalline			x		x			x	x		x		x					x			x			Highly crystalline		
Antistatic										x		x		x										Antistatic		
Presence of plasticizer			Phthalate-free	Phthalate-free	No	No	No	No	No	No	No	No	No	No	Phthalate-free	No	No	No	No	No	No			Presence of plasticizer		

Further technical data about individual products plus best practice advice for handling and processing our elastomers is available by contacting your local sales representative or by visiting our online product finder tool:
<http://www.huntsman-tpu.com/>

Infinite scope for innovation

AVALON® TPUs: Key products



Physical properties			55 AHG	65 AK-ESD	80 AHT	85 ABR	90 AHT	90 ABR	95 AHT	95 ABR	60 DB	65 DB		Physical properties	
	Norm	Unit	AVALON® ester-based				AVALON® ester-based				Unit	Norm			
GENERAL			GENERAL												
Hardness	ISO 7619	Shore A	54	65	80	86	90	89	94	94	-	-	Shore A	ISO 7619	Hardness
Hardness	ISO 7619	Shore D	-	-	30	37	42	44	48	47	59	64	Shore D	ISO 7619	Hardness
Density	ISO 1183-1	g/cm³	1,14	1,18	1,21	1,20	1,21	1,21	1,21	1,22	1,23	1,23	g/cm³	ISO 1183-1	Density
MECHANICAL			MECHANICAL												
Tensile strength	DIN 53504	MPa	12	30	30	50	47	50	55	50	55	60	MPa	DIN 53504	Tensile strength
Elongation @ break	DIN 53504	%	650	850	600	600	500	500	480	500	470	400	%	DIN 53504	Elongation @ break
Tensile stress @ 100% elongation	DIN 53504	MPa	1,6	2,5	5	5,8	7	8,9	15	12,8	19	25	MPa	DIN 53504	Tensile stress @ 100% elongation
Tensile stress @ 300% elongation	DIN 53504	MPa	3,5	5	8	12	12	19	25	23,7	31	300	MPa	DIN 53504	Tensile stress @ 300% elongation
Tear strength	ISO 34-1	N/mm	30	45	70	80	95	80	118	105	175	200	N/mm	ISO 34-1	Tear strength
Compression set 70h @ 23°C	ISO 815	%	-	25	-	20	-	25	-	30	35	35	%	ISO 815	Compression set 70h @ 23°C
Compression set 24h @ 70°C	ISO 815	%	-	-	-	-	-	-	-	-	65	65	%	ISO 815	Compression set 24h @ 70°C
Abrasion	ISO 4649	mm³	45	< 100	40	20	40	20	35	25	30	30	mm³	ISO 4649	Abrasion
OTHER FEATURES			OTHER FEATURES												
Transparent				x	x		x		x						Transparent
Improved abrasion resistance						x		x		x					Improved abrasion resistance
Antistatic				x											Antistatic
Presence of plasticizer			Phthalate-free	Phthalate-free	No	No	No	No	No	No	No	No			Presence of plasticizer

HG - High Gloss; HT - High transparency; K - Crystal, Transparent ; ESD - ESD adjusted; R - Abrasion improved.

Further technical data about individual products plus best practice advice for handling and processing our elastomers is available by contacting your local sales representative or by visiting our online product finder tool:

<http://www.huntsman-tpu.com/>

Global elastomers experts

Committed to customers: We build partnerships with our customers and work across an international network of R&D and manufacturing locations to help solve complex challenges and deliver the highest levels of technical support and customer care.

Committed to quality: Wherever we are, whatever we are doing, we prioritize environmental, health and safety protection, and we are always rigorous about quality control and assurance.

Committed to innovation: We keep pace with the most innovative trends in plastics processing by using the latest equipment and making regular investments in our formulation, manufacturing and R&D capabilities.

Committed to sustainability: We create solutions that contribute to a more sustainable society by helping to conserve energy, preserve natural resources and reduce our overall carbon footprint.



HUNTSMAN

Enriching lives through innovation

EUROPE

Everslaan 45
3078 EVERBERG
BELGIUM
Phone: +32 2 758 92 11

Elastomers_EAIME@huntsman.com

USA

10003 Woodloch Forest Dr
The Woodlands, TX 77380
Phone: +1 281 719 6000

Elastomers_Americas@huntsman.com

CHINA

No 479 Wen Jing Road
Minhang Development Zone
Shanghai 200245
Phone: +86 21 3357 6527

Elastomers_APAC@huntsman.com

www.huntsman.com

About Huntsman:

Huntsman Corporation is a publicly traded global manufacturer and marketer of differentiated and specialty chemicals with 2018 revenues of more than \$9 billion. Our chemical products number in the thousands and are sold worldwide to manufacturers serving a broad and diverse range of consumer and industrial end markets. We operate more than 75 manufacturing, R&D and operations facilities in approximately 30 countries and employ approximately 10,000 associates within our four distinct business divisions.

Huntsman Corporation warrants only that its products meet the specifications stated in the sales contract. Typical properties, where stated, are to be considered as representative of current production and should not be treated as specifications. While all the information presented in this document is believed to be reliable and to represent the best available data on these products, HUNTSMAN MAKES NO WARRANTY OR GUARANTEE OF ANY KIND, EXPRESS OR IMPLIED, INCLUDING BUT NOT LIMITED TO ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, NON-INFRINGEMENT OF ANY INTELLECTUAL PROPERTY RIGHT OF ANY THIRD PARTY, OR WARRANTIES AS TO QUALITY OR CORRESPONDENCE WITH PRIOR DESCRIPTION OR SAMPLE, AND ANY USER OF PRODUCTS DESCRIBED HEREIN SHOULD CONDUCT A SUFFICIENT INVESTIGATION TO ESTABLISH THE SUITABILITY OF ANY PRODUCT FOR ITS INTENDED USE AND ASSUMES ALL RISK AND LIABILITY WHATSOEVER RESULTING FROM THE USE OF SUCH PRODUCT, WHETHER USED SINGLY OR IN COMBINATION WITH OTHER SUBSTANCES. Products may be toxic and require special precautions in handling. For all products described herein, the user should obtain detailed information on toxicity, together with proper shipping, handling, and storage procedures, and should comply with all applicable safety and environmental standards. The behavior, hazards and/or toxicity of the products referred to in this publication in manufacturing processes and their suitability in any given end-use environment are dependent upon various conditions such as chemical compatibility, temperature, and other variables, which may not be known to Huntsman. It is the sole responsibility of the user of such products to evaluate the manufacturing circumstances and the final products under actual end-use requirements and to adequately advise and warn future purchasers and users thereof.

AVALON®, CASTECH™, DALTOCAST®, IROGRAN® and TECNOTHANE® are registered trademarks of Huntsman Corporation or an affiliate thereof in one or more, but not all, countries. Copyright © 2019 Huntsman Corporation or an affiliate thereof. All rights reserved.